# Innovative Thermal Management Concepts for Space Vehicles

B. Esser\*, M. Kuhn\*\*, I. Petkov\*\*, V. Hannemann\*\*\*, J. Barcena<sup>†</sup>, C. Jimenez<sup>†</sup>, A. Okan<sup>††</sup>, S. Ontaç<sup>††</sup>, L. Haynes<sup>‡</sup>, S. Gianella<sup>‡‡</sup>, A. Ortona<sup>§</sup>, M. Barbato<sup>§</sup>, L. Ferrari<sup>§</sup>, V. Liedtke<sup>§§</sup>, D. Francesconi<sup>†</sup>, M. Portaluppi<sup>†</sup> and H. Tanno<sup>##</sup>
\*DLR (German Aerospace Center), Institute of Aerodynamics and Flow Technology, 51147 Köln, Germany
\*\*DLR (German Aerospace Center), Institute of Structures and Design, 70569 Stuttgart, Germany
\*\*\*DLR (German Aerospace Center), Institute of Aerodynamics and Flow Technology, 37073 Göttingen, Germany
\*\*\*DLR (German Aerospace Center), Institute of Aerodynamics and Flow Technology, 37073 Göttingen, Germany
<sup>†</sup>Tecnalia, Industry and Transport Division, Mikeletegi Pasealekua 2, 20009 San Sebastian, Spain
<sup>††</sup>TUBITAK UZAY, ODTU Kampusu, 06800 Balgat, Ankara, Turkey
<sup>‡</sup>Fluid Gravity Engineering Ltd, The Old Coach House, 1 West Street, Emsworth, Hants PO10 7DX, United Kingdom
<sup>‡‡</sup>Erbicol SA, Viala Pereda 22, 6828 Balerna, Switzerland
<sup>§</sup>Scuola Universitaria Professionale della Svizzera Italiana, ICIMSI, Galleria 2, 6928 Manno, Switzerland
<sup>§§</sup>Aerospace and Advanced Composites GmbH, Viktor-Kaplan-Str. 2, 2700 Wiener Neustadt, Austria
<sup>#</sup>Thales Alenia Space Italia Spa, Strada Antica di Collegno 253, 10146 Torino, Italy

##JAXA (Japan Aerospace Exploration Agency, Kakuda Space Center, Kakuda Miyagi 981-1525, Japan

### Abstract

Future aerospace transportation demands solutions that exceed the performance of current systems and up-to-date material limits. Therefore, new and disruptive solutions must be envisaged to meet those extreme conditions. In the search of new solutions for sharp leading edges of the future hypersonic reentry or transport vehicles, the THOR project, composed of 8 European organizations (industries, research centres and universities) and one Japanese Agency (JAXA), is actively working on definition, design, implementation, and simulation of new passive and active thermal management solutions and their verification in relevant environment (high enthalpy facilities).

The paper provides an overview of the recent developments on the four concepts that are targeted in the project, applying different physical methodologies:

- Passive cooling using highly conductive carbon-based fibres
- Passive cooling with intensive internal radiative exchange
- Active cooling using a ceramic sandwich-TPS with ceramic foams
- Active transpiration cooling of external surfaces

Details on these thermal management concepts, requirements from end users, test configurations as well as results from experimental and numerical verification are given.

#### **1. Introduction**

Thermal protection systems (TPS) are required in order to protect the internal structure and payloads of space vehicles entering a planetary atmosphere from outer space. There are several examples such as manned orbiters like the space shuttle, probe missions or planetary exploration missions, e.g. to Mars.

For this purpose it is necessary to protect the vehicle from all heat generated during re-entry. This can be carried out by proper design as well as selection of appropriate high temperature materials. There are many different possibilities, but the final selection depends on the vehicle's entry velocity, its shape and size, its entry trajectory and the properties of the atmosphere. The research project THOR funded within the EU FP7 programme is targeting at improvements of the thermal management for CMC-based thermal protection systems. In case of a passive TPS, state-of-the-art thermal management is based on local heating conditions which are in a quite straightforward procedure used to determine the main parameters of thermal protection, resulting in the typical blunted geometries.

The classical local thermal management concept does not account for significant gradients of thermal loads along the surface. Such gradients, however, are expected to become significant for future space vehicles as well as for some concepts of hypersonic transport vehicles, which are currently being considered. Most of these vehicles are basing on an improved aerodynamic performance which requires a reduction of bluntness, in particular at the wings' leading edges. Accordingly, the regions with lowest radius of curvature and highest thermal loads get reduced in size and become immediately surrounded by areas with a substantially lower loading. The absolute values of the maximal heat fluxes, however, will increase significantly with a reduced radius of curvature.

A set of mission scenarios and general requirements on potential evolutions of hypersonic applications (beyond 2020) have been specified by Thales Alenia Space. The step-wise approach has consisted of outlining the end-user needs, to bridge the current atmospheric re-entry technologies towards the settlement of actually considered configurations (see Figure 1):

- Short-medium term developments: A reference application deemed as evolution of the European state-ofthe-art in Space Entry Vehicles technology and its current industrial capabilities,
- Medium-long term development: Evolutions in Space Entry Vehicle technologies, altogether in parallel to nowadays technological investigations of novel propulsion technologies,
- Future applications: Hypersonic vehicles (speed in the range of Mach greater than 5).



Figure 1: Actually considered configurations for atmospheric entry and hypersonic transport.

Based on the trade-off of different missions it was concluded that a wing leading edge was defined as baseline configuration to be studied in THOR, to satisfy the requirements for future vehicles, where re-usability on winged bodies is demanded and the use of hot structures based on ceramic matrix composites is a must. Nevertheless, in the case of vehicles with nearly sharp leading edges it seems that passive thermal protection will exceed the current application limits of those materials (i.e., heat fluxes up to  $2 \text{ MW/m}^2$ , leading to temperature peaks of 2200 K), even with a global thermal management. Therefore, also thermal management technologies with active cooling are considered and going to be verified in THOR.

# 2. Thermal Management Concepts

For systems with considerable load gradients the classical local thermal management must be considered a zeroth order solution only. Therefore, the local concept is not being followed in the frame of THOR. It is being replaced by more global thermal balances that consider thermal loadings along the complete surface of a vehicle or one of its components. A leading edge geometry was selected as reference geometry for the project.

The global approach is supposed to provide more realistic thermal data which allow for increasing the tolerable heat loads while maintaining the actual operating limit temperatures of CMC surface materials. In addition, appropriate physical and technological measures are considered that support the global approach in order to improve the performance of thermal protection systems by

- equilibration of thermal loading by transferring heat efficiently from highly loaded surface areas to less loaded regions, or
- reduction of surface temperatures by means of active cooling.

The consideration of global thermal management concepts is encouraged by progress in base material development. New materials with tailored properties are available for being integrated into thermal protection systems, as e.g.

- pitch-based fibres with a huge thermal conductivity which exceeds the conductivity of conventional fibres by at least one order of magnitude, as well as
- SiC-based ceramic foams and lattices with minor damage tolerance but operational temperatures being very close to those of conventional dense ceramic matrix composite (CMC) materials.

Experimentally, a significant potential has been observed and validated for the reduction of surface temperatures by the long-distance thermal exchange capabilities of thermal radiation and transpiration cooling of external surfaces.

These developments and results are investigated in order to quantify their specific potential with regard to the objectives, i.e. equilibration of thermal loads and reduction of surface temperatures. In total, four different concepts are being considered, grouped into passive cooling concepts and active cooling. Within each group, two separate thermal concepts are investigated. Each concept is going to be developed in detail, transferred and implemented into hardware, and validated experimentally in high enthalpy facilities and numerically by coupled simulations in parallel.

### 2.1 Passive Cooling Concepts

Efficient thermal equilibration is the principal objective for the thermal management concepts using passive cooling technologies. The thermal load balance shall be improved by transferring heat from highly loaded areas to regions with a lower thermal loading. Of course, the potential of passive cooling technologies is restricted when being compared with active cooling. Nevertheless, it is useful to identify and quantify the potential, because passive cooling does not require integration of any additional auxiliary systems for space application. The two considered passive cooling concepts are:

- Concept 1a: Innovative composite materials with integrated highly conducting fibres.
- Concept 1b: TPS structures with intensive radiative heat exchange

In concept 1a the heat conduction capability of the TPS skin is being improved by integrating highly conductive fibres into the ceramic matrix. Conventionally, fibres with a conductivity of 10 to 20 W/mK are being used. There are, however, pitch-based carbon fibres with a reported thermal conductivity of up to 600 W/mK. An increase of the fibres' conductivity by at least one order of magnitude is expected realistic. The influence on the effective thermal conductivity of the composite was analysed by Reimer et al. [1]. The results shown in Figure 2 were obtained under the assumption that the fibres' conductivity of a CMC material can considerably be improved when using fibres with a high conductivity.

Concept 1b is approaching thermal equilibration by heat exchange below the TPS skin. Advantage is taken from the long-distance thermal exchange capabilities of thermal radiation. According to the Stefan-Boltzmann relation, radiated heat strongly intensifies with temperature and therefore intrinsically supports thermal equilibration on a nonuniformly loaded curved structure. The potential of this mechanism for conventional CMC-based thermal protection had been found from thermal tests on a flat plate configuration [2].



Figure 2: Effective thermal conductivities [2]

#### 2.1 Active Cooling Concepts

Active cooling is an attractive option, since it provides the potential of carrying away large amounts of heat or preventing heat loads to impinge. The method, however, adds complexity to the system, since it requires additional system components, as e.g. coolant storage, supply and return pipes. Therefore, active cooling has not been favorised for space vehicles in the past, and for the future it is supposed that active cooling is considered only if passive cooling concepts are not sufficient to keep a thermal protection system within its operational limits.

The two active cooling concepts which are considered in THOR are:

- Concept 2a: Sandwich-TPS with ceramic foams,
- Concept 2b: Transpiration cooling.

The two concepts reflect the two different technical approaches that are principally used to actively cool a highly loaded surface by leading the coolant either along the back side of the hot surface or pushing it through a porous segment immediately to the external surface.

In concept 2a, a novel ceramic sandwich structure, as it had been described in [3], is being considered. In its most general form it is made of two ceramic skin layers and a silicon carbide based ceramic foam in between, as shown in Figure 3. When applied in a TPS structure, one of the CMC layers would be identical to a vehicle's external CMC skin. The foam, which might be replaced by a lattice structure, is highly porous and therefore well-suited to pass the coolant along the back side of the external skin to highly loaded regions where it takes over the heat convectively, additionally reducing the surface temperature, taking advantage of the increased surface for heat exchange and of the high thermal conductivity of the SiC based struts as well.



Figure 3: Sketch of ceramic sandwich.

The cooling principle of concept 2a is based on convective cooling. Accordingly, there is no necessity to specifically demonstrate the physical validity of this thermal management approach. Nevertheless, there are technological challenges which are mainly related to finding the optimal morphology of the foam and identifying suitable joining techniques for the interface of foam and external CMC skin.

For transpiration cooling in concept 2b, the coolants are supposed to be fed through porous surface elements to the exterior. In this case, cooling is achieved not only for the porous element itself, but also for regions downstream of transpired surface parts. Transpiration cooling had successfully been applied for CMC-based structures in various

research projects, e.g. RESPACE [4] and FAST20XX [5], with gaseous as well as liquid coolants. Transpiration cooling does not require a closed loop for the coolant. Therefore, the auxiliary infrastructure is not as complex as required for an application of the ceramic sandwich in concept 2a.

There is one major drawback of transpiration cooling, since the emanating coolant might considerably interfere with the boundary layer that established on the external surface. Depending on the type of coolant and its flow rate the coolant is able to trigger boundary layer separation or initiate boundary layer transition. At flight relevant Mach and Reynolds numbers both phenomena are potentially associated with highly intensified heat loads in the wake of the porous segment leading to a considerable reduction or even reversion of global thermal performance.

# 3. Test Configurations

As a result from the general assessment of future requirements a leading edge geometry was selected for experimental and numerical verification in the frame of the THOR project. Two geometries are being considered. The "baseline geometry" includes a leading edge with a nose radius of 20 mm. A smaller nose radius of 10 mm was chosen for the second option. The principal setup for experimental verification is identical for both geometries. As sketched in Figure 4a, the assemblies are mounted on a water-cooled base plate (1). Common elements are the TPS structure (2), a copper connector (3) as well as CMC side (4) and rear walls (5).



(a) Baseline geometry (R = 20 mm)





A conventional passively cooled TPS structure is considered as reference concept "0". It is sketched in Figure 4b. In this case, the TPS structure (2) consists of the external skin only, prepared with conventional CMC material. In addition to the components illustrated in Figure 4a, a block of insulation material (6) is filling the space between CMC skin and water-cooled base-plate in order to minimize thermal losses to the interior. The sketch in Figure 4b is describing the test configuration of concept 1a as well. The CMC skin of this configuration, however, is being prepared with integrated highly conductive fibres which are aligned parallel to the surface.

For concept 1b, internal radiation will be enabled by removing the insulation block used for concepts "0" and 1a, either partially or completely. The CMC skin is made of conventional standard CMC. In a fully passive version, the insulation is being removed in the curved part only as sketched in Figure 5. It allows radiative heat exchange for thermal equilibration in the nose region.



Figure 5: Test configuration for concept 1b (fully passive version).

When removing the insulation block completely, the internal radiation can further be intensified. Since the CMC skin can radiate to the water-cooled base plate, the concept is not a fully passive one anymore, but becomes semi-active. The semi-active version is described by the sketch in Figure 4a. It is considered as limiting case only, since such a high visibility of actively cooled parts seems unrealistic for an application, as e.g. a leading edge or a nosecap. By replacing the standard CMC with a CMC prepared with highly conductive fibres, concepts 1a and 1b can be combined.

Concept 2a is aiming for active convective cooling of the CMC skin from the backside. This is achieved by integration of a ceramic Si-SiC lattice as a central part of a sandwich which the coolant can be passed through. As shown in Figure 6, the lattice (7) is covering the backside of the external CMC skin in the nose region. It also extends downstream for some distance along the top surface providing additional potential for thermal equilibration. Along this additional length, the lattice will tightly be joined to the CMC skin.



Figure 6: Test configuration for concept 2a.

A block of insulation material (6) is used to form a channel for the coolant flow along the CMC skin. The upper leg of the copper connector (3) will be adapted to the length of the foam in order to keep the external geometry of the foam simple. In a basic preparatory step, optimal manufacturing process and lattice morphology were identified by Erbicol and SUPSI. The selected lattice morphology, which is shown in Figure 7, was characterised concerning its fluid dynamical and mechanical properties.



Figure 7: CMC lattice for concept 2a.

To identify the optimal joining technique for the interface of lattice and external CMC skin, a trade-off study was initiated. Starting from five initial processing routes, three were preselected to be further assessed, which include the use of:

- High temperature adhesives based on SiC (commercially available),
- Pre-ceramic polymers (Polysilasane), mixed with different fillers (Si; SiC, MAX phases) to promote beneficial reaction and improve the stability and performance,
- Similar to the previous, where phenolic resin is used instead of the pre-ceramic polymers.

While the first method is based on a quite easy processing route (application and curing at 90°C), the last two methods involve a rather complex route with several steps: curing at autoclave, pyrolysis and final treatment at temperatures above 1400 °C under controlled atmosphere conditions. The basic performance of the joining

techniques and subsequent optimization of the process is determined by pull-off tests and microstructural analysis. Base materials and joined specimen for the pull-off tests are shown in Figure 8.



Figure 8: Base materials and specimen for joint characterization

The final selection among the three candidate routes will be determined by specific mechanical tests on shear strength at high temperature in the laboratories of AAC. A non-standard procedure has been designed in order to properly test the reliability of the joint. A 3D sketch of the test setup is shown in Figure 9. It includes a rectangular (50 x 27.5mm) sample representing the CMC skin. The samples are prepared by Erbicol from SiC/SiC material with a thickness of 2 mm (see Figure 8a). The lattice (see Figure 8b), consisting of 3 layers of 8 hexagonal cells, is connected at the bottom of the sample. The cell size is identical to the cells that are going to be used for the L3K test hardware. Accordingly, the results from joint characterization can immediately be transferred to the test hardware.



Figure 9: Test setup for final joint characterisation

During the tests the external surface of the SiC/SiC sample is being heated by radiation. In parallel, a mechanical load is applied by a graphite piston to the bottom side of the lattice, which is introducing a shear load to the joint. Two results will be obtained from the test, i.e.

- The upper application temperature of the particular joint, and
- The shear strength at the design temperature level, i.e. the temperature which is expected for the L3K test hardware is in joined area.

The design temperature level will be determined from the thermal tests in L3K on concept 0. It is supposed to be below 1573 K which is considered as upper temperature.

Additional characterization tests are foreseen to determine the properties of the new CMC materials developed in the frame of the project, i.e.

- the SiC/SiC material for the CMC skin of concept 2a,
- the C/SiC material with integrated highly conductive fibres used for the CMC skin of concept 1a.

The tests include mechanical properties (tensile, compression, interlaminar shear strength and bending) according to proper standards (ASTM and EN) and thermophysical properties (thermal diffusivity, specific heat) at room temperature and at elevated temperature levels.

The second active cooling concept, i.e. concept 2b, is aiming at the transpiration of a coolant through the CMC skin, in order to locally decrease the surface temperature. The coolant is penetrating a porous segment that is integrated into the TPS structure towards the exterior. As shown in Figure 10, an insert made of porous C/C (8) will be incorporated into the curved area of the CMC skin (2) in order to provide a permeable passage for gaseous coolants. The system requires a coolant supply system with a coolant reservoir attached to the porous segment.



Figure 10: Test configuration for concept 2b.

It had been mentioned before that transpiration cooling is associated with the risk of significant boundary layer interference. The interference with the boundary layer cannot be investigated in combination with the thermal validation of the concept in an arc-heated facility, but must be investigated at realistic and flight relevant Mach and Reynolds numbers. In the frame of THOR, a corresponding test campaign is foreseen in JAXA's high enthalpy shock tunnel HIEST. A geometrically simple test setup is favourable for such tests. A planar configuration is much better suited than curved one. Accordingly, the tests in HIEST are using a flat plate as shown in Figure 11.



(a) HIEST flat plate



Figure 11: Test setup for the transpiration cooling campaign in HIEST.

In the upstream part there is a removable insert which can be equipped with a porous segment for transpiration cooling. The porous segment can be inserted flush bound into the flat plate. Coolant is supplied from a manifold below the flat plate. Measurements are foreseen in the wake of the porous segments. Heat flux and pressure measurements are performed by coaxial thermocouples and pressure transducers installed along the center line of the flat plate. In particular, the heat flux distribution is providing information about boundary transition. An extension plate with additional sensors (pressure transducers and thermocouples) is attached to the front plate to obtain data up to a location nearly 1000 mm downstream of the porous segment.

The interaction between external flow and emanating coolant is visualized by high-speed Schlieren photography. Tests are performed at several test conditions with different enthalpy, from low enthalpy (3.5 MJ/kg) to high enthalpy (15 MJ/kg). Different gaseous coolants are going to be applied with the flow rate as additional test parameter. In addition to Nitrogen, which is considered as baseline coolant, Helium is applied.

# 4. Experimental Verification

Thermal validation tests are designated to be carried out in DLR's arc heated facility L3K. L3K is one of the two test legs of the LBK facility which has been playing an important role for decades in the qualification and testing of TPS components and materials. Particular experience has been established in validation of fluid-structure interaction phenomena. The test environment at L3K is particularly prepared for thermal measurements. Included are temperature measurements at specific locations in the interior of a model with several types of thermocouples, as well as surface temperature measurements. Pyrometers are used for local measurements, in addition surface temperature distributions on a complete model surface can be recorded with infrared camera systems.

Test conditions were selected from the set of the facility's standard operating conditions. One main criterion was applied for the selection: the test conditions should allow to perform tests on the reference concept "0", made of conventional passively cooled CMC, without exceeding the material's operational limit temperatures. Two conditions, named THOR-1 and THOR-2, were considered. Both are associated with a gas mass flow rate of 142 g/s, the total enthalpy is 11.7 MJ/kg for THOR-1 and 11.0 MJ/kg for THOR-2. Based on a preparatory numerical study [6], condition THOR-2 was selected as baseline test condition. For variation of the heat load gradient, the configurations are tested at two angles of attack, 10° and 20°. While the maximal heat load at the stagnation line is supposed to be nearly identical for both angels, the average heat load on the model's top surface is lower for an inclination of 10°. Therefore, this configuration is associated with a higher load gradient.

The first experimental campaigns were carried out for the reference concept "0" and the two passive cooling concepts 1a and 1b. Test assemblies were prepared with the baseline geometry having a nose radius of 20 mm. Photographs of the test assembly are given in Figure 12. The CMC leading edge had been prepared with grooves for thermocouple integrated. In total, 14 thermocouples had been installed, 8 of them along the symmetry line and three on each side in a distance of 60 mm to the symmetry line. Surface temperatures were measured with pyrometers at 4 spots along the symmetry line, each spot just above a thermocouple location. In addition, surface temperature distribution was recorded by an infrared camera system.



(a) CMC hardware

(b) Test assembly in the L3K test chamber

Figure 12: Experimental setup.

The test assembly for the reference concept was prepared with conventional CMC parts. For the tests related to concept 1a, the conventional CMC leading edge was replaced by another leading edge with integrated highly conductive fibres. With a value of 220 W/mK, the fibres' thermal conductivity was about one order of magnitude higher than the conductivity of the conventional fibres.

As shown in Figure 13a, the interior of the model was completely filled with insulation material for the tests related to the reference concept and to concept 1a. For concept 1b, the internal setup was changed to the configuration shown in Figure 13b, with a cavity opened behind the leading edge that provides visibility for the radiative heat exchange. Each configuration was tested at test condition THOR-2 with different angles of attack, 10° and 20°. The test duration was 180 seconds, which is sufficient to achieve steady-state conditions on the surface of the leading edge. Repeatability tests were included for each configuration to check the reproducibility of measured data.





(a) reference concept and concept 1a

Figure 13: Model interior.

(b) concept 1b (passive version)

Figure 14 shows results of three thermocouple measurements in the nose region, comparing the reference configuration with concept 1b at a model inclination of 10°. All three thermocouple are placed on the symmetry line, the streamwise location is indicated in Figure 14d. When opening the cavity for concept 1b, TC 1 on the backside of the stagnation point and TC 3 below the upper surface are immediately affected, while TC 4 remains covered by insulation material. With open cavity, the temperature indicated by TC 1 drops by 95 K, while TC 3 indicates a temperature increase of 85 K. So, the temperature difference between TC 1 and TC 3, which amounts to 376 K in the reference configuration, is reduced to 194 K with open cavity, clearly demonstrating a positive effect of thermal equilibration for this passive configuration. The Thermocouple TC 4 is hardly affected by the cavity. The difference between the two configurations is 14 K.



Figure 14: Cavity effect on thermocouple measurements (conventional CMC,  $\alpha = 10^{\circ}$ ).

A comparison of the surface temperature measurements at the stagnation point is plotted in Figure 15, again for a model inclination of  $10^{\circ}$ . Compared with the reference, the passive version of concept 1b provides a temperature

reduction from  $1500^{\circ}$ C to  $1420^{\circ}$ C. This difference is considerable in terms of heat fluxes. According to the temperature reduction, the cavity effect enables the surface to sustain higher heat fluxes. With a reduction of 80 K, the heat flux might be increased by 17%.

The same comparison is shown in Figure 15b for the leading edge prepared with highly conductive CMC. Here, a temperature of 1430°C was measured at the stagnation point with radiation blocked. This case refers to concept 1a. Accordingly, concept 1a provides a temperature reduction of 70 K, allowing for an increase of heat flux by 15%. When additionally opening the cavity, stagnation point temperature further reduces to 1397°C. Accordingly, the combined application of concepts 1a and 1b allows for an increase of the heat flux at the stagnation point which is 21% above the heat flux at radiative equilibrium.



Figure 15: Cavity effect on stagnation temperature measurements (CMC,  $\alpha = 10^{\circ}$ ).

### 5. Numerical Verification

In addition to the experimental verification in high enthalpy facilities the four thermal concepts are going be verified numerically by coupled simulations related to the test configurations. Well established simulation tools are being applied for flow and structure. Two flow solvers, i.e. DLR's TAU [7] and FGE's TINA codes, are available for the simulation of the high enthalpy flows in the two facilities. Both are validated Navier-Stokes solvers, being capable to take into account chemical as well as thermal non-equilibrium states for the fluid. During the project's conceptual phase the TAU code had been applied in a preparatory study to identify the best suited operating conditions in L3K, as described in the previous section. The simulation of the thermomechanical response of the structure is carried out with commercial codes, e.g. ANSYS and MSC PATRAN.

Another preparatory numerical analysis was performed in order to determine the dimensional character of the leading edge test configurations. In particular the validity of the assumption, that a two-dimensional analysis is sufficient, should be checked. In this context, 2D and 3D computations of the flow field around the leading edge model were carried out. For simplification, a radiative equilibrium boundary condition was set on the model's surface. Some results are plotted in Figure 16. Figure 16a is showing some temperature isolines on the model surface. Starting at the symmetry plane on the left, the isolines are running in lateral direction mainly. Deviations from this trend are observed in close vicinity to the model's surface temperature distributions in several cutting planes are plotted and compared with the results of a 2D simulation. Except for the cut at y = 0.09 m, i.e. in 7 mm distance to the sidewall, all curves appear coincident with the 2D result.

For coupled simulations, a loosely coupled strategy is applied. Starting from an initial distribution of convective heat fluxes, e.g. based on radiative equilibrium at the surface, the resulting surface temperatures are computed by the structural code. This result is transferred to the flow solver to correct the convective heat fluxes for the next iteration. Generally, the procedure converges within a few iterations. As an example, an intermediate results of the surface temperature distribution is shown in Figure 17. The plot refers to the thermal response of the leading edge model for the passive version of concept 1b (see Figure 12a and Figure 13b).



(a) 3D view of temperature isolines and streamlines

(b) surface temperatures distributions

Figure 16: Numerical results of a 3D flow simulation assuming radiative equilibrium at the model surface.



Figure 17: Surface temperature distribution for the passive version of concept 1b (result from a coupled simulation).

A slightly different approach is followed for the numerical simulations related to the active cooling concept 2a. This configuration is the most complex one. In addition to the external flow it includes a complex internal flow that heavily interacts with the CMC skin and with the ceramic lattice. For the coupling with the external flow, an aerothermodynamic database (ATDB) is used. The database can be prepared in advance and provides the link between surface temperature and heat flux rate. The data were generated from several simulations with the TINA code. Heat fluxes and surface temperatures were determined for non-catalytic and super-catalytic surface conditions at several L3K flow conditions and for various model inclinations. For the non-catalytic case, Figure 18 exemplarily shows the heat flux distribution for radiative equilibrium conditions at test condition THOR-2, compared with the results of two isothermal wall conditions.

For concept 2a, detailed simulations of the flow inside the CMC sandwich structure were carried out in order to identify the optimal flow path for the coolant and to check the performance of this concept. Radiative equilibrium conditions were used for the thermal load on the external surface. For the baseline test configuration three different flow paths were considered. The results were compared with regard to the overall temperature level, the lateral homogeneity of the surface temperatures and the prevention of recirculation zone within the lattice. Best results were obtained for a flow path following the contour of the leading edge, with an inlet at the bottom and outlet at the top surface as sketched in Figure 19. The surface temperature shows a homogeneous distribution in lateral direction with only minor variations close to the sides. Using air as coolant with a flow rate of 2.5 g/s, a maximal surface temperature of 1630 K is achieved, which is considerably below the radiative equilibrium temperature of about 1900 K (see Figure 16b).



Figure 18: Non-catalytic heat flux distributions at test condition THOR-2.





### 6. Conclusions

The FP7 project THOR is targeting new thermal management concepts for atmospheric space entry and hypersonic transport vehicles. A leading edge has been selected as reference configuration and corresponding requirements were collected. Four different concepts (two passive and two active) are being traded-off, by simulation and testing in order to obtain a proof-of solution after a verification campaign.

The first passive concept 1a, using a CMC containing highly conductive pitch-based carbon fibers, shows conclusive evidences of improved thermal equilibration, both numerically and experimentally. The second passive concept 1b uses cavities to enhance balancing of thermal loads by internal radiation. Experimental results indicate a significant potential for thermal equilibration. The first active concept 2a envisages the use of ceramic porous structures to drive and promote heat exchange with a coolant gas by means of convective cooling. Sound joining with CMC walls is a key issue. Numerical simulation is quite encouraging, joining and assembly activities are on-going. The second active concept 2b is addressed to transpiration cooling, where a porous C/C insert will be integrated into the test configuration for experimental verification in L3K (DLR) and the Hiest shock tunnel (JAXA). Preliminary tests at DLR demonstrated feasibility of the concept and preliminary tests at JAXA were conducted successfully.

### 7. Acknowledgements

The research leading to these results has received funding from the European Union Seventh Framework Programme (FP7/2007-2013) under grant agreement  $N^{\circ}$  312807.

### References

- [1] Reimer, T., I. Petkov, and W. Rotärmel, 2015. Numerical Investigation of the Thermal Benefit of Using a High Thermal Conductivity CMC for the Leading Edge of Hypersonic Vehicles, *Proc. 8th European Symposium on Aerothermodynamics of Space Vehicles*, ESA Publications Division, European Space Agency, Noordwijk, The Netherlands.
- [2] Willems, S., B. Esser, and A. Gülhan, 2015. Experimental and numerical investigation on thermal fluidstructure interaction on ceramic plates in high enthalpy flow, accepted for publication in *CEAS Space Journal*.
- [3] Ortona, A., S. Pusterla, and S. Gianella, 2011. An integrated assembly method of sandwich structured ceramic matrix composites, *Journal of the European Ceramic Society*, 31(9): 1821-1826.
- [4] Kuhn, M. and H. Hald, 2008. Application of Transpiration Cooling for Hot Structures, in: Gülhan, A. (Ed.), RESPACE – Key Technologies for Reusable Space Systems, *Notes on Numerical Fluid Mechanics and Multidisciplinary Design*, Springer, 98:82-103.
- [5] Reimer, T., B. Esser, and A. Gülhan, Arc Jet Testing of CMC Samples with Transpiration Cooling (2013). 44<sup>th</sup> AIAA Thermophysics Conference, San Diego, USA, AIAA 2013-2904.
- [6] Esser, B., A. Gülhan, T. Reimer and I. Petkov, 2015. Experimental Verification of Thermal Management Concepts for Space Vehicles. *Proc. 8th European Symposium on Aerothermodynamics of Space Vehicles*, ESA Publications Division, European Space Agency, Noordwijk, The Netherlands.
- [7] Schwamborn, D., T. Gerhold, and R. Heinrich. 2006. The DLR TAU-Code: Recent Applications in Research and Industry. in: P. Wesseling, E. Onate and J. Periaux. *European Conference on Computational Fluid Dynamics, ECCOMAS CFD 2006*, TU Delft, The Netherlands.